

INNOVA COLLECTION SOFFIT

ABOUT

Simpson INNOVA SOFFIT – a premium solution designed to protect and enhance the eaves of your home or building. Our soffit products provide superior ventilation, durability, and aesthetic appeal, making them an essential component for maintaining the structural integrity and visual appeal of your property.



BASIC USE INFORMATION

Simpson's fiberglass reinforced foam panels are designed for quick and efficient installation, reducing labor costs and project timelines. The interlocking panel system allows for seamless integration, minimizing thermal bridging and air infiltration. These panels can be used in a wide range of residential, multi-family, and commercial applications, offering versatility in design and construction. They can be installed over various substrates, including wood framing, concrete, and masonry, making them suitable for new construction as well as renovation projects.

TEXTURES

INNOVA provides textured finish panels replicating classic looks like stucco and granite. SOFFIT is offered in two textures. SMOOTH delivers an ultra-sleek glass-like finish, and WOODGRAIN offers a classical wood appearance with far less hassle.

MANUFACTURER

Simpson Panel
30851 US Hwy. 278
Addison, AL 35540
www.simpsonpanel.com/

PRODUCT TESTING INFORMATION

Structural Evaluation Pensacola Testing Laboratory

QAI Laboratories ASTM E84-17a Fire Resistance Certified

Miami Dade County Approved:
NOA No. 23-0314.08



COLORS

SW 7705 Pure White	SW 7551 Greek Villa	SW 7008 Alabaster	SW 7012 Creamy	SW 7036 Accessible Beige
SW 6142 Macadamia	SW 7029 Agreeable Gray	SW 7017 Dorian Gray	SW 0023 Pewter Tankard	SW 0037 Morris Room Gray
SW 7039 Virtual Taupe	SW 0006 Tale Red	SW 7592 Crabby Apple	SW 7728 Green Sprout	SW 7734 Olive Grove
SW 6156 Connected Gray	SW 9130 Evergreen Fog	SW 7605 Gale Force	SW 6244 Naval	SW 7046 Anonymous
SW 7048 Urbane Bronze	SW 7020 Black Fox	SW 7674 Peppercorn	SW 7069 Iron Ore	SW 6358 Tricorn Black

	ASTM Test Method	Units of measure	Units of measure
Simpson MC15 Panel	ASTM C271 Density	15 Lb/Cu. Ft.	
	ASTM C365 Core Compressive	356 psi Strength	4061 psi Modulus
	ASTM C273 Core Shear	250 psi Strength	4298 psi Modulus
	ASTM D790 Flexural Properties	1166 psi Strength	39380 psi Modulus
	ASTM E84-17a Flame Spread	15 (<25) Flame Spread Index	450 (<450) Smoke Developed Index